

FIG. 1




FIG. 2

Figure 3

Abrasion Cycles

Material	0		1000		5000		10,000		40,000	
	Weight (g)	Weight Loss (g)	Weight (g)	Weight Loss (%)	Weight (g)	Weight Loss (g)	Weight (g)	Weight Loss (g)	Weight (g)	Weight Loss (%)
Current Soft Rubber	27.933	0	27.497	0.436	25.488	2.445	21.932	6.001	17.406	37.69
Coated SPECTRA®	7.353	0	7.162	0.191	6.8	0.553	6.622	0.731	5.74	21.94
Present Invention # 1	18.823	0	18.603	0.22	18.532	0.291	18.417	0.406	17.819	5.334
Present Invention # 2	17.476	0	17.342	0.134	17.286	0.19	17.124	0.352	16.438	5.94




FIG. 4A




FIG. 4B